ALTURA UV MATT

700.648

Description

One-component, alkyd-urethane matt transparent varnish, with exceptional gloss retention, resistance to the marine environment and UV stability.

Use

Recommended for use as a matt varnish on all type of wooden surfaces, interior and exposed exterior.

Informations

Finish	Matt	
Colours	.000 Colourless	
Pack	0,75 l	
Solids by Volume	45 ± 2%	ISO 3233-2
Specific Gravity	0,90 – 0,94 g/cm^3	ISO 2811-1
Flash Point	32 °C	ISO 3679
VOC	379 g/l	Calculated
Shelf Life	36 months	

Application

SURFACE PREPARATION

The humidity content in the wood must be below 18%. All surfaces must be perfectly clean, dry and free of oil, contaminants and old painting before application of recommended products.

NEW BUILD

Complete sanding with sandpaper grade P120 - P180. Remove all traces of dirty, oil, resin. Take special care to remove any residual sand dust or dirt from the wood pores by using dry air or alcohol. 24 hours after the product application, lightly abrade with sandpaper grade P320-P400.

MAINTENANCE

Remove all trace of contamination, grease and oil by high pressure freshwater cleaning. Proceed with degreasing or solvent cleaning if necessary and repeat freshwater cleaning. All surfaces must be clean, dry and free of contaminants. Remove old dark watermarks with T-Bleaching or alternatively, hydrogen peroxide 80 volume. Remove all loose/poor adhered paint and varnishes by abrading with sandpaper grade P180 - P240. In case the wood pieces are glued, sand in both directions. Take special care to remove any residual sand dust or dirt from the wood pores by using dry air or alcohol.

Sanding between coats with Scotch-Brite grade fine.

How to Apply

Standard 	Brush and roller
Conventional Spray 	Pressure 3,5 bar Nozzle 1,2 – 1,4 mm

Film Thickness per Coat

DFT	Recommended: 30 µm Standard application range: 20 - 30 µm
WFT	Recommended: 70 µm Standard application range: 45 -70 µm

ALTURA UV MATT

700.648

Additional Application Information

Theoretical spreading rate	Application range at the recommended thickness: 30 µm – 15 m2/l
Thinner	703 – Roller/Brush (15% max) 703 – Conventional spray (15% max)

Application notes

Dilute the first coat of ALTURA UV MATT between 5-15%. Number of coats will depend on the wood absorption, generally between 2 and 5.

General notes

Given recoating times are indicative, as it can vary according to actual thickness applied, weather conditions, painting plan and project size.

Compatibility

Previous Coat

Biowood - Polywood

Subsequent Coat

N.A.

Drying Time

	10 °C		15 °C		20 °C		30 °C	
	Min	Max	Min	Max	Min	Max	Min	Max
Overcoating interval	N.A.	N.A.	24 h	7 days	18 h	7 days	16 h	7 days
Sanding	N.A.	N.A.	36 h	36 h	24 h	24 h	24 h	24 h
Complete drying	N.A.	N.A.	7 days	7 days	7 days	7 days	5 days	5 days

N.B. The drying times and the overcoating intervals increase with higher thickness of the applied paint film. Always check the existing paint film is dry before applying any further product coats.

Conditions during application

During application and curing:
Ambient temperature: minimum 15 °C, maximum 30 °C.
Minimum substrate temperature 10 °C (if during the curing the temperature drops below 10 °C, overcoating will take additional time).
Avoid the formation of condensation, the surface temperature should be at least 3 °C above dew point.
Maximum relative humidity 80%.
Painting area should be well ventilated during application and drying/curing.

Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, check that the container is closed during the storage and the temperature is between 5 °C and 35 °C.
Avoid exposure to direct sunlight.

ALTURA UV MATT

700.648

Safety Rules

Comply with the provisions set by the local health and safety at work regulations. Avoid contact with the skin, operate in well-ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application use appropriate PPE - Personal Protections Equipment (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

INSTRUCTIONS FOR THE DISPOSAL OF THE BIOCIDAL PRODUCTS AND PACKAGING
Empty packaging containing biocidal products: disposal of empty packaging according to the requirements of the waste disposal law, for example by taking them to the recycling centre. Packages containing the unused biocidal product: Dispose of the product not used in accordance with the law of disposal of such waste, for example by taking it to a recycling centre, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses.
INSTRUCTIONS FOR THE SAFETY SECURITY OF THE BIOCIDAL PRODUCTS AND PACKAGING
Empty containers and containers still containing the biocidal product: Packaging must be disposed of as hazardous waste under the full responsibility of the holder of such waste. Do not empty into drains or watercourses.

Disclaimer

The values indicated in the present technical sheet can have slight variations from one batch to another. The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The wet film thickness refers to the undiluted product. In case of dilution, this value increases. The above information is the result of accurate laboratory tests and practical experience, however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. can only guarantee their quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A. directly. The present datasheet annuls and replaces every other precedent to this one.