SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Idrofis

ZIDNA AKRILNA EMULZIJA NA BAZI VODE ZA UNUTARNJE RADOVE



COD. 4700006

IDROFIS - V.2024-09-24

OPIS

IDROFIS je akrilna emulzija na bazi vode za impregnaciju unutarnjih zidova. IDROFIS prodire u zidnu površinu, zapunjujući poroznosti u žbukama, pripremajući tako idealnu podlogu za naredne slojeve boje, izolirajući ih od alkalnosti betonskih i sličnih podloga.

POGODNE PODLOGE

Može se nanositi na:
- Nove ili stare vapneno/cementne žbuke.
- Betonske podloge.
- Gips i gipsane ploče.
- Stare organske i mineralne boje ili obloge koje su suhe, čvrste i srednje upojnosti.
- Razne mineralne podloge koje su barem srednje upojnosti.

Zidne površine treba prikladno pripremiti prateći upute koje nalazimo pod " PRIPREMA PODLOGE".
Ne smije se nanositi na svježe podloge.

TEHNIČKI PODACI

-Vrsta veziva: Kopolime rstiren-akrilan u vodenoj disperziji.
-Volumenska masa UNI EN ISO 2811-1: 1,01 ± 0,05 kg/l
-Sušenje (pri 25 °C i 65% di R.V.): na dodir 30-40 min.; nanošenje drugog sloja nakon najmanje 14 sati.

PRIPREMA PODLOGE

- Potpuno odstraniti pljesan, isoljavanje, stare neprijanjajuće slojeve boje, prašinu i sl. Po potrebi pregletati površinu.
- Na potpuno čistu i suhu podlogu nanijeti jedan sloj IDROFISA. Nakon cca. 12-14 sati nanijeti završni sloj.

UPUTSTVA ZA NANOŠENJE

- Uvjeti okoline i podloge:
Temperatura okoline: Min. +8 °C / Max. +35 °C

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia
info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Relativna vlaga okline: <75%
Temperatura podloge: Min. +5 °C / Max. +35 °C
Vlažnost podloge: <10%
-Izbjegavati nanošenje u prisutnosti površinske kondenzacije.
- Alat: kist, valjak, prskalica.
- Broj slojeva: najmanje dva sloja.
- Proizvod se razrijeđuje promjenjivo u ovisnosti o upojnosti podloge, u svakom slučaju ne manje od 1 dijela emulzije sa 6 dijelova vode. Pravilno razrijeđeni proizvod na zidu daje lagani polusjajni efekt. Premalo razrijeđen može prouzrokovati teškoću boje kod prianjanja, dok previše razrijeđen može prouzrokovati razliku u upojnosti podloge te veću potrošnju boje.
- Čišćenje alata: sa vodom neposredno nakon upotrebe
- Prosječna potrošnja: 50-60 m2 /l za svaki sloj kod nanošenja na srednje upojne podloge. Preporuča se definiranje potrošnje prethodnom probom za svaku specifičnu podlogu posebno.

NIJANSIRANJE

- - - - -

SKLADIŠTENJE

Maksimalna temperatura skladištenja: +30°C
Minimalna temperatura skladištenja: +5°C
Proizvod je najbolje upotrijebiti u roku od 2 godine od datuma proizvodnje, ako se čuva u originalnoj neotvorenoj ambalaži i pri odgovarajućoj temperaturi skladištenja.

SIGURNOSNA UPOZORENJA

Granična vrijednost EU (Dir. 2004/42/EZ)
Kat. A/h: Vezujući temeljni premazi (baza voda): 30 g/l (2010)
Ovaj proizvod sadrži max: 30 g/l HOS

Koristiti porizvod prema važećim propisima o higijeni i sigurnosti; ne bacati ambalažu u okoliš nakon uporabe; ostatke ostaviti da se dobro osuše i postupati kao s posebnim otpadom. Ne ispuštati ostatke u kanalizaciju, vodne tokove ili tlo. Za dodatne informacije pročitati sigurnosne listove.

SAN MARCO GROUP guarantees that the information herein is provided to the best of its technical and scientific knowledge and based on its experience; nonetheless, the company may not be held liable for the results obtained using these products, as application conditions are beyond its control. It is recommended to always make sure that the product is suited to each specific instance. The present sheet voids and replaces any previously existing sheets.